



## StanZoil NK-22 382

Chemical Product	CAS #	BTT (minutes)	Permeation level	Standard	Degradatio level	Rating
1,1,1-Trichloroethane 99%	71-55-6	23	1	ASTM F739	3	=
1,1,2,2-Tetrachloroethane 98%	79-34-5	20	1	ASTM F739	1	-
1,2 - dichloroethane 99%	107-06-2	7	0	ASTM F739	1	-
1,2-Dichlorobenzene 99%	95-50-1	16	1	ASTM F739	1	-
1,2,4-Trichlorobenzene 99%	120-82-1	37	2	ASTM F739	1	-
2-Butoxyethanol (Butyl Cellusolve) 99%	111-76-2	295	5	ASTM F739	4	++
2-Ethoxyethanol (Cellosolve) 99%	110-80-5	265	5	ASTM F739	4	++
2-Ethoxyethyl acetate (Cellosolve Acetate) 99%	111-15-9	42	2	ASTM F739	3	+
2-Methylpentamethylenediamine 99%	15520-10-2	100	3	ASTM F739	3	++
2-Propanol (Isopropanol) 99%	67-63-0	480	6	ASTM F739	4	++
2,2,2-Trifluoroethanol 99%	75-89-8	480	6	ASTM F739	4	++
Acetaldehyde 99%	75-07-0	8	0	ASTM F739	4	=
Acetic acid 10%	64-19-7	480	6	ASTM F739	4	++
Acetic acid 50%	64-19-7	480	6	ASTM F739	4	++
Acetic acid 99%	64-19-7	289	5	ASTM F739	4	++
Acetone 99%	67-64-1	9	0	ASTM F739	3	=
Acetonitrile 99%	75-05-8	37	2	ASTM F739	4	+
Acrylonitrile 99%	107-13-1	16	1	ASTM F739	4	+
Ammonium hydroxide solution 29%	1336-21-6	148	4	ASTM F739	4	++
Aniline 99%	62-53-3	102	3	ASTM F739	3	++
Benzene 99%	71-43-2	5	0	ASTM F739	1	-
Butyl Acetate 99%	123-86-4	12	1	ASTM F739	1	-
Carbon disulfide 99%	75-15-0	2	0	ASTM F739	4	=
Carbon Tetrachloride 99%	56-23-5	12	1	ASTM F739	1	-
Chromic Acid 50%	7738-94-5	268	5	ASTM F739	4	++
Cumene 98%	98-82-8	15	1	ASTM F739	3	=

\*not normalized result

### Overall Chemical Protection Rating

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

- Used for **high chemical exposure** or chemical immersion, limited to BTT based on a working day.
- Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative BTT based on a working day.
- **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.
- **Not recommended**, these gloves are deemed suitable for work with this chemical.

   NT : Not tested

   NA : Not applicable because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time, such as concentration and temperature, glove thickness and glove reuse, may also affect performance. Other glove requirements, such as length, dexterity, cut, abrasion, puncture and snag resistance, or glove grip also need to be considered in making your final selection.

## StanZoil NK-22 382

Chemical Product	CAS #	BTT (minutes)	Permeation level	Standard	Degradatio level	Rating
Cyclohexane 99%	110-82-7	50	2	ASTM F739	3	+
Dichloromethane (Methylene Chloride) 99%	75-09-2	2	0	ASTM F739	3	=
Diethanolamine 97%	111-42-2	480	6	ASTM F739	4	++
Dimethylformamide 99%	68-12-2	26	1	ASTM F739	3	=
Dimethylsulfoxide 99%	67-68-5	346	5	ASTM F739	4	++
Ethanol 95%	64-17-5	363	5	ASTM F739	4	++
Ethyl acetate 99%	141-78-6	5	0	EN 374-3:2003	NT	NA
Ethylene glycol 99%	107-21-1	480	6	ASTM F739	4	++
Formaldehyde 37%	50-00-0	480	6	ASTM F739	4	++
Furfural 99%	98-01-1	51	2	ASTM F739	3	+
Hydrazine 35%	302-01-2	480	6	ASTM F739	4	++
Hydrazine 70%	302-01-2	480	6	ASTM F739	4	++
Hydrochloric acid 10%	7647-01-0	480	6	ASTM F739	4	++
Hydrochloric acid 35%	7647-01-0	NT	NT		4	NA
Hydrochloric acid 37%	7647-01-0	480	6	ASTM F739	4	++
Hydrogen bromide 47%	10035-10-6	480	6	EN 374-3:2003	NT	NA
Hydrogen fluoride Anhydrous 99%	7664-39-3	71	3	ASTM F739	NT	NA
Isobutyl alcohol 99%	78-83-1	480	6	ASTM F739	4	++
Kerosene mixture	8008-20-6	463	5	ASTM F739	4	++
m-Cresol 97%	108-39-4	480	6	ASTM F739	4	++
Methanol 85%	67-56-1	NT	NT		4	NA
Methanol 99%	67-56-1	67	3	ASTM F739	4	++
Methyl Amyl Ketone 98%	110-43-0	15	1	ASTM F739	3	=
Methyl Ethyl Ketone (2-Butanone) 99%	78-93-3	8	0	ASTM F739	2	-
Methylisobutylketone 99%	108-10-1	23	1	ASTM F739	3	=
n-Heptane 99%	142-82-5	63	3	ASTM F739	4	++

\*not normalized result

### Overall Chemical Protection Rating

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

- Used for **high chemical exposure** or chemical immersion, limited to BTT based on a working day.
- Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative BTT based on a working day.
- **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.
- **Not recommended**, these gloves are deemed suitable for work with this chemical.

  NT : Not tested

  NA : Not applicable because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time, such as concentration and temperature, glove thickness and glove reuse, may also affect performance. Other glove requirements, such as length, dexterity, cut, abrasion, puncture and snag resistance, or glove grip also need to be considered in making your final selection.

## StanZoil NK-22 382

Chemical Product	CAS #	BTT (minutes)	Permeation level	Standard	Degradatio level	Rating
n-hexane 95%	110-54-3	34	2	ASTM F739	4	+
N-methyl-2-Pyrrolidone 99%	872-50-4	38	2	ASTM F739	1	-
N-N dimethyl acetamide 99%	127-19-5	27	1	ASTM F739	2	=
Naphtha Heavy mixture	68551-17-7	480	6	ASTM F739	4	++
Naphtha VM&P mixture	8032-32-4	25	1	ASTM F739	4	+
Nitric acid 10%	7697-37-2	480	6	ASTM F739	4	++
Nitric acid 20%	7697-37-2	480	6	ASTM F739	4	++
Nitric acid 40%	7697-37-2	480	6	ASTM F739	4	++
Nitric acid 50%	7697-37-2	480	6	ASTM F739	4	++
Nitrobenzene 99%	98-95-3	26	1	ASTM F739	2	=
Pentane 99%	109-66-0	31	2	ASTM F739	3	+
Phenol 85%	108-95-2	305	5	ASTM F739	4	++
Phosphoric acid 75%	7664-38-2	480	6	ASTM F739	4	++
Phosphoric acid 85%	7664-38-2	480	6	ASTM F739	4	++
Potassium Hydroxide 50%	1310-58-3	480	6	ASTM F739	4	++
Pyridine 99%	110-86-1	9	0	ASTM F739	1	-
Sodium hydroxide 20%	1310-73-2	480	6	ASTM F739	4	++
Sodium hydroxide 40%	1310-73-2	480	6	ASTM F739	4	++
Sodium hydroxide 50%	1310-73-2	480	6	ASTM F739	4	++
Sulfuric acid 10%	7664-93-9	480	6	ASTM F739	4	++
Sulfuric acid 40%	7664-93-9	480	6	ASTM F739	4	++
Sulfuric acid 50%	7664-93-9	480	6	ASTM F739	4	++
Sulfuric acid 96%	7664-93-9	115	3	ASTM F739	1	-
Toluene 99%	108-88-3	1	0	EN 374-3:2003	NT	NA
Triethanolamine 98%	102-71-6	480	6	ASTM F739	4	++
Triethylamine 99%	121-44-8	22	1	ASTM F739	3	=
Turpentine mixture	8006-64-2	137	4	ASTM F739	3	++

\*not normalized result

### Overall Chemical Protection Rating

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

- Used for **high chemical exposure** or chemical immersion, limited to BTT based on a working day.
- Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative BTT based on a working day.
- **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.
- **Not recommended**, these gloves are deemed suitable for work with this chemical.

   NT : Not tested

   NA : Not applicable because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time, such as concentration and temperature, glove thickness and glove reuse, may also affect performance. Other glove requirements, such as length, dexterity, cut, abrasion, puncture and snag resistance, or glove grip also need to be considered in making your final selection.

## StanZoil NK-22 382

Chemical Product	CAS #	BTT (minutes)	Permeation level	Standard	Degradatio level	Rating
Unleaded gasoline mixture	8006-61-9	10	1	ASTM F739	1	-
Xylene 99%	1330-20-7	8	0	ASTM F739	1	-

\*not normalized result

### Overall Chemical Protection Rating

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

- Used for **high chemical exposure** or chemical immersion, limited to BTT based on a working day.
- Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative BTT based on a working day.
- **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.
- **Not recommended**, these gloves are deemed suitable for work with this chemical.

  NT : Not tested

  NA : Not applicable because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time, such as concentration and temperature, glove thickness and glove reuse, may also affect performance. Other glove requirements, such as length, dexterity, cut, abrasion, puncture and snag resistance, or glove grip also need to be considered in making your final selection.